

Water
Oil
Solvent

Product information

Product Description An uncoated paper for line drawings and check prints with simple fills

Physical Properties

Grammage	75 g/m ²	Acidity	PH 7,5 ± 1
Thickness	102 µm	Whiteness CIE	159
Reflection R457 +UV	109 %	Reflection R457 - UV	83 %
Opacity	92 %	Stiffness MD	140 mN
Stiffness CD	55 mN	Porosity	820 ml/min
Roughness WS	240 ml/min	Roughness TS	260 ml/min
Moisture content	4,9 %	L*: a*: b*	94,1 : 3,5 : -16,4

Storage Conditions Best results are obtained between 20 ± 3°C and 50 ± 5 % RH.

Available Widths (mm)

2" core	297 mm	420 mm	594 mm	610 mm	625 mm	841 mm	914 mm	1067
Length	120 m	120 m	120 m	50 m	50 m	50/91/120 m	50/91 m	50m

Storage Conditions Best results are obtained between 20 ± 3°C and 50 ± 5 % RH.

Printer Compatibility

Please refer to mediaguide.oce.com

Lamination Compatibility

Hot	Warm	Cold	
1	1	3	Hot, heat activated: 105 °C – 130 °C
			Warm, heat activated: 85 °C – 95 °C
			Cold, pressure sensitive

3 = excellent 2 = fair 1 = not recommended

Outdoor Use Designed for indoor use.

Colour Profiles Océ develops high-quality colour profiles for media / ink / toner / printer / RIP combinations. Check availability of profiles for your printer on the download section of www.mediaguide.oce.com.



“From sustainably managed forests – For more info: www.pefc.org”