

Photo Papers

Toner

Water

(eco) Solvent

UV Curable

Latex

IJM252 Smart Dry Photo Paper, Satin - FSC® 200 g/m²

Product Description

Satin, FSC and Fogra-certified, high-quality photo paper with an instant-dry, microporous ceramic coating, on a PE-coated base.

Physical Properties

Thickness (µm)	204 ± 6	ISO 534	Whiteness CIE	100	D65/10°
Weight (g/m ²)	198 ± 7	ISO 536	L*; a*; b*	93.0; -0.4; -2.8	
Opacity (%)	> 89		Gloss (60°) (%)	17 ± 5	

Applications/features

High-quality photos
Indoor signage (posters, point of purchase)
Exhibition graphics
Short-term outdoor signage (when laminated)
Instant dry
Excellent colour reproduction
High colour density and image sharpness
Perfect ink control and absorption
Suitable for dye and pigment inks
Smudge resistant
Dimensionally stable and excellent lay-flat
Excellent lamination properties
Fogra certified
FSC certified

Available Widths (mm)

2"core	432	610	914	1067	1118	1270	1372	1524		
--------	-----	-----	-----	------	------	------	------	------	--	--

Refer for our current offering to mediaguide.oce.com

Storage Conditions

Shelf life: 1 year, Temperature 23°C, Relative Humidity 50%
Keep out of direct sunlight and repack opened rolls when not in use.

Print Conditions

Best results are obtained at 23°C and 50% RH.

Environment, Health & Safety

No Material Safety Data Sheet required. Paper waste not suitable for recycling.

Lamination Compatibility

Cold	Warm	Hot	Cold: pressure sensitive
yes	yes	no	Warm: heat activated: 85°C - 95°C
			Hot: heat activated: 105°C -130°C


Outdoor Use

This photo paper is not recommended for outdoor use.

Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations. Check availability of profiles for your printer on mediaguide.oce.com

Certification



Processing Guidelines

Printing guidelines

Side to be printed is the outer side of the roll. Allow material to adapt to room conditions for 24 hours before printing. Dye inks on micro-porous coated products can exhibit fading (apart from UV) due to its open structure. Gasses like Ozone cause this phenomenon. Lamination will solve this issue.

Lamination guidelines

Reverse side adhesion excellent for mounting and encapsulation applications. Encapsulation is not recommended. One-sided lamination may cause curl.

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.